

परीक्षण / अंशांकन रिपोर्ट TEST / CALIBRATION REPORT

संख्या / No. ETDC (MH) T 2 M / 2 9 0 /

दिनांक Dated 28 0 5 2 0 1 3



भारत सरकार

Government of India संचार एवं सूचना प्रौद्योगिकी मंत्रालय

Ministry of Communications & Information Technology सूचना प्रौद्योगिकी विभाग

Department of Information Technology मानकीकरण, परीक्षण एवं गुणवत्ता प्रमाणन निदेशालय

Standardisation, Testing & Quality Certification Directorate इलेक्ट्रानिकी परीक्षण तथा विकास केन्द्र

Electronics Test & Development Centre

बी-108, फेज-8, औद्योगिक क्षेत्र, एस.ए.एस. नगर, मोहाली-160 071 (पंजाब)

B-108, Phase VIII, Industrial Area, S.A.S. Nagar, Mohali 160 071 (Punjab) दूरभाष / Telephone : 0172- 2236711, 2237576, 2237030, फैक्स/Fax : 0172- 2236681

ई-मेल/email : etdcmh @ stqc.nic.in, etdc @sancharnet.in वेबसाइट/Web site: www.stqc.nic.in



No.:	ETDC(MH)/T&M/ 290	Dated: 28.05.2013	Page: 1 of 6
1.	Indentor's Address	Okaya Power Ltd. D-7, Udyog Nagar, Near Peeragarhi Metro Stat New Delhi.	ion Services
2.1 2.2 2.3 2.4 2.5	Description of item(s) Nomenclature Make/Model Sr. No. Manufactured by Quantity	: SMF / VRLA Battery : OKAYA/ OB 28-12 : Sample No.1 to 3 (Rest : SUNOXX INTERNAL : Three.	
3.	Sample(s) received on	: 16.01.2013	
4.	Condition of sample(s) on receipt	: Good	
5.	Date(s)/Period item(s) tested	: 17.01.2013 to 28.05.2	2013
6.	Location where test(s) carried out (With name and address)	: ETDC Mohali	
7.	Reference of test method(s) used	: JIS C 8702 -1 : 2003 as	nd Indentor's.
8.	Applicable product specification(s)	: JIS C 8702 -1 : 2003 a	nd Indentor's.
9. 10.	Deviation(s), exclusion(s), addition(s) in test method(s) Environmental conditions	: Nil	
10.1	Temperature	: $25^{\circ}\text{C} \pm 10^{\circ}\text{C}$	

10.2 Humidity : 45 % to 70 %

11. Statement with regard to compliance : Refer to test results (Test Data)

12. Statement on uncertainty in : Not Applicable.

measurement

13. Major Equipment Used

S. no.	Nomenclature	Make	Model	Cal. Validity	
1.	ELECTRONIC LOAD	Digitronics	750W	March, 2014	
2.	MULTIMETER (DIGITAL)	RISHABH	15S	Jan, 2014	
3.	High Rate Discharger	SIMAKANS	400A	Used as source	
4.	Clamp meter	Meco	3600	Aug,2013	
5.	Measuring Tape	Freemans	15M	Aug,2014	
6.	Weighting Scale	Modern Business	SNEW-100	July, 2013	
7.	Stop Watch	Timeter	J-23	Jan,2014	
8.	Vibration Test Machine	Sarswati Dynamics	SEV 100	Jan,2014	

OI/C (Test)

Approved by Head (Test)

ssued by (Customer Service Cell)



No.: ETDC(MH)/T&M/290 Dated: 28.05.2013 Page: 2 of 6

14. RESULTS SUMMARISED:

Test Stage	Test Requirements (Cl. Ref. of specs.)	Test Condition	Test Data	Pass/ Fail (Qty.)	Uncertainty (Where applicable)
1. Visual Examination	•	There shall not be any deformation of body and cracks / corrosion on the terminals of the sample (Sealed Lead Acid Battery).	No defects observed.	Pass	
Marking		As given below			
2.1 Polarity Cl: 4.4 JISC:	Cl. 6.1 of JIS C 8702-2, Cl.	Positive and negative terminals of the sample shall be marked with	Positive: Symbol (+) (With Red colour)	Pass	-
8702	4.4 of JIS 8702-1	symbols (+) and (-) respectively.	Negative: Symbol (-) (With Black colour)		4. 46
2.2 Designation Cl : 4.3	Cl. 6.2 of JIS 8702-2, Cl.	The sample shall be marked with relevant details :			- 7/e)
	4.3 of JIS C 8702-1	a) Type Designation.	SMF / VRLA Battery	Pass	
	, 6	b) Nominal Voltage (n x 2.0 V)	12V	Pass	
		c) Rated Capacity (20 Hr. rate)	28Ah	Pass	
		d) Manufacturer.	Sunoxx International	Pass	1
		e) Year and Month of Manufacture.	Jan 2013	Pass	
2.3. Additional Information	4.3 of JIS C 8702-1	Following parameters shall be determined in respect of the sample: a) Mass (Kg)	Sample No Mass(Kg) 1. 8.20 2. 8.19	-	• 1 e)
			3. 8.16		
		b) Dimension (LxWxH) (cm)	Sample No LxWxH(mm) 1. 17.6 x 16.5 x 12.5 2. 17.6 x 116.5 x12.5 3. 17.6 x 116.5 x12.5		
		c) Charging Current / Voltage	Stand By Use 13.5 - 13.8 V (20 °C) Initial current 7.8 A	-	-
			Cycle use 14.4 - 15.0 V (20 °C)		Y (2)

Tested by OI/C (Test)

Approved by Rumen Head (Test)



Issued by (Customer Service Cell)



No.: ETDC(MH)/T&M/ 290 Dated: 28.05.2013 Page: 3 of 6

14. RESULTS SUMMARISED:

Test Stage	Test Requirements (Cl. Ref. of specs.)	Test Condition	Test Data	Pass/ Fail (Qty.)	Uncertainty (Where applicable)
3. Classification of Battery (Sample No.1,2,3)	Cl. 7 of JIS C 8702-2	The sample shall either be Prismatic or Cylindrical.	Prismatic.	Pass	-
4. Capacity Test (20Hrs.) (Sample No.1)	Cl. 5.1 and 7.1 of JIS C 8702-1/2003	The Fully charged sample shall be discharged by at a constant current of $1.4 \text{ A} \pm 2 \%$ at an ambient temperature of $25^{\circ}\text{C} \pm 2^{\circ}\text{C}$ till an end point terminal voltage of 10.5V (6 x 1.75V). The capacity shall be 28 Ah or more.	Capacity observed: 29.89 Ah (First cycle)	Pass	· Comp
(Sample No.2)			Capacity observed: 29.17 Ah (First cycle)	Pass	1)
(Sample No.3)			Capacity observed: 30 Ah (First cycle)	Pass	
5. High Rate Discharge Test (Sample No.2)	Cl. 5.2 and 7.2 of JIS C 8702- 1/2003	Fully charged sample shall be discharged at a constant current of 28A (20 x I ₂₀) upto an end point terminal voltage of 9.6V (6x1.6V). The discharge duration shall be 27 minutes or more.	Discharge time: 32 minutes	Pass	-
6. Maximum Permissible Current (Sample No.3)	Cl. 5.5 and 7.5 of JIS C 8702/1	Fully charged sample shall be discharged at a constant current as under: 56A (40 x I ₂₀) for 300s After the discharge, sample shall be recharged and it shall be discharged at a constant current of 56 A (40*(I ₂₀)) upto an end point terminal voltage of 8.04 V (6*1.34 V) The discharge duration shall not be less than 150 sec.	814seconds.	Pass	-

Tested by OI/C (Test)

Approved by Rumor Head (Test) Services and Servi

Issued by (Customer Service Cell)



No.: ETDC(MH)/T&M/ 290 Dated: 28.05.2013 Page: 4 of 6

Test Stage	Test Requirements (Cl. Ref. of specs.)	Test Condition	Test Data	Pass/ Fail (Qty.)	Uncertainty (Where applicable)
7.Charge Retention Test (Sample No.1)	Cl.5.4 &7.4 JISC:8702	Fully charged sample shall be stored for 120 days. After the period, the capacity test shall be performed at a constant discharge current of 1.40A(I ₂₀) upto an end point terminal voltage of 10.5V. The capacity shall not be less than 75%		Pass	
		of the rated capacity			- 2
8. Charge Acceptance Test after Deep Discharge (Sample No. 03)	JIS C 8702 Cl. 5.6	A suitable load resistor which can draw a current of 56 A ± 10% (40xI20) shall be connected across the fully charged sample and it shall be stored for 360Hrs. After the storage period, the load resistor shall be disconnected from the sample and sample shall be recharged at constant voltage (Uc) for a period of 48 Hrs with initial charging current between 8.4 A to 14 A (6 x I20 to 10 x I20). After the charging period ,the sample shall remain open circuited for 5 to 24Hrs. and then shall be discharged with constant current 1.40A (I20)	Test conducted.	Pass	
		The observed capacity of the sample shall not be less than 75% of the rated capacity	103.07%		
09. Gas Recombination Efficiency (Sample no. 3)	JIS C 8702-1 Cl. 5.8	Fully charged sample shall be charged continuously at a constant current $(2xI_{20})$ for 48 Hrs. Within one hour the sample shall be charged at a constant current of $(0.1xI_{20})$	Test Conducted	Pass	·
		Immediately after lapse of 24 Hrs. from current passing, the gas shall be collected for 5 Hours at ambient temperature 25 ±10°C. The gas recombination efficiency of the sample shall be 90% or more.	96.59%	, ,	

Tested by OI/C (Test)

Approved by Runner Head (Test) Runner Issued by (Customer Service Cell)



No.: ETDC(MH)/T&M/290 Dated: 28.05.2013 Page: 5 of 6

14. RESULTS SUMMARISED(Contd.):

Test Stage	Test Requirements (Cl. Ref. of specs.)	Test Condition	Test Data	Pass/ Fail (Qty.)	Uncertainty (Where applicable)
10. Resistance to Vibration (Sample No. 3)	JIS C 8702-1 Cl.5.9	The sample shall be subjected to the following conditions: Frequency: 16.7Hz Amplitude: 4mm (peak to peak) Duration: 1 Hr continuous Direction: Vertical, Longitudinal and lateral (X, Y & Z) State of sample: Fully charged.	Conducted.	Pass	
		After the above test, there shall not be any deformation, mechanical damage, breaking on the sample	No visual defects deformation, mechanical damage, breaking on the sample observed.		4, .
11. Resistance to Shock (Sample No. 3)	JIS C 8702-1 Cl 5.10	The fully charged sample shall be given three falls from a height of 20cm with bottom facing downward on a flat hard wooden plate of 10 mm or more in thickness.	Conducted.	Pass	-
		There shall not be any deformation, mechanical damage, breaking on the sample	No visual defects deformation, mechanical damage, breaking on the sample observed.		

15. Additional Remarks:

1.

Sample No	Serial No
1	IQWGSO1200002456
2	IQWGSO1200002457
3	IQWGSO1200002458

- 2. Maximum Permissible current as per cl no. 5.5 is conducted only on $I_m = 40 \times I_{20}$ as per the facility available and customer request.
- This test report supersede the earlier interim test report No.ETDC(MH)/T&M/290 dated 01.02.2013
- 4. Device under test (DUT) Photograph enclosed as Annexure-I

Tested by OI/C (Test)

Approved by Head (Test)

Issued by (Customer Service Cell)

बिनय राजपूत VINAY RAJPUT वैज्ञानिक 'सीं' / Scientist 'C' संचार एवं जुबना प्रौद्योगिकी यंत्रालय Ministry of Comm. & Info. Tech भारत सरकार, इटीडीस, बहाली (क.) Govt. of India, ETDC, Mohali (Pb.)



No.: ETDC(MH)/T&M/ 290

Dated: 28.05.2013

Page: 6 of 6





Figure-I




Figure-II




Figure-III

Issued by Customer Service Cell

